

# MALLA

Fibreglass mesh: an essential reinforcement in specific applications.

## Composition

Fibreglass mesh, with alkaline protection, woven, 5x5mm. and with a weight of 80 gr/m2.

## Application field:

Ideal for:

- Absorb the efforts that occur during the drying of waterproof coatings or mortars such as HYDROMAR SUPERFLEX.
- Ideal for corners and joints.
- Ideal for continuous thicknesses and precise consumption of cement.

## Recommendations for use:

Should not use mesh:

- For uses other than those detailed in this technical file.
- In products that do not require it.

## Technical data:

Product	Technical data	GLASS FIBRE FABRIC (Standard ETAG 004)
Features	Warp	136 TEX
	Warp	136 TEX
	Long traction resistance.	750 N / 5 cm
	Tranction resistance. Breakpoint	850 N / 5 cm
	Length	1600 N / 5 cm
	Lengthening	2-4%

To know the security precautions related to the use, storage and elimination of the product, consult the Security Datasheet available on the website: [www.aymarsa.es](http://www.aymarsa.es)

NOTE: The information contained in this technical file is based on our expertise and specialized laboratory trials. The characteristics of the resulting product will depend on the correct preparation and application in situ by the user. If these conditions are not met, it will not be possible to obtain the results indicated above.



Factory and offices

Ctra. C-35, Km 58 · Ap. correus nº1  
08470 SANT CELONI (Barcelona)

Tel. (+34) 93 867 00 00

aymar@aymarsa.es  
[www.aymarsa.es](http://www.aymarsa.es)

